

<b>Application</b>	Hot-melt adhesive used for side seams in the Graphic Arts Industry														
<b>Properties</b>	It can be applied by roller, wheel and jet application systems														
<b>Technical Data</b>	<table border="1"> <tr> <td>Base:</td> <td>EVA</td> </tr> <tr> <td>Colour</td> <td>Tan</td> </tr> <tr> <td colspan="2">Viscosity Brookfield CAP2000</td> </tr> <tr> <td>160 °C</td> <td>ca. 3800 mPas</td> </tr> <tr> <td>190 °C</td> <td>ca. 1700 mPas</td> </tr> <tr> <td colspan="2">Softening point (R&amp;B)</td> </tr> <tr> <td></td> <td>ca. 80 °C</td> </tr> </table>	Base:	EVA	Colour	Tan	Viscosity Brookfield CAP2000		160 °C	ca. 3800 mPas	190 °C	ca. 1700 mPas	Softening point (R&B)			ca. 80 °C
Base:	EVA														
Colour	Tan														
Viscosity Brookfield CAP2000															
160 °C	ca. 3800 mPas														
190 °C	ca. 1700 mPas														
Softening point (R&B)															
	ca. 80 °C														
<b>Instructions for use</b>	Between 170 °C and 190 °C. Open time and Setting time vary according to the operating conditions.														
<b>Health &amp; Safety</b>	Please check the product material safety data sheet.														
<b>Cleaning</b>	For regular flushing: use Swift@clean.100 For thorough cleaning: use Swift@clean.400														
<b>Other</b>	<p>Storage: One year under normal ambient conditions i.e. 15 °C to 35 °C, dust-free. Can withstand frost.</p> <p>Components of this product have US FDA approval under 21 CFR section 175.105.</p> <p>Additional technical information is available upon request.</p> <p>Any change in operating conditions or substrates should be notified. The customer should consult with our technical department before any change.</p>														

Indications and advice herein are based on our own and (or) outside research and are believed to be correct.  
However, they are given for information only and we cannot be held responsible unless so stipulated in particular terms of sale.  
We request that purchasers carry out their own tests to confirm if our products are suitable for their anticipated use.  
The Purchaser has the ultimate responsibility for the consequences for the use of these products.  
Nothing herein shall be understood as being permission to operate under licence or to infringe any existing patent  
Our responsibility is limited to the supply of products of the correct quality as described to the Forbo Customer.  
Forbo will not accept responsibility for any change of operating conditions carried out without notification.